

ATERRA

Wood Look 8x48


TILE

AMERICA

SHADE VARIATION



V3 - Moderate Variation While the colors present on a single piece of tile will be indicative of the colors to be expected on the other tiles, the amount of colors on each piece may vary significantly. For example "that little bit of color" on one piece of tile may be the primary color on the next piece.



WEAR CODE

Gesso & Juta: Rated 5 for All Residential and Commercial Application. Grafite, Tabacco & Cuoio: Rated 4 for All Residential and Light Commercial Applications.

NORM

ISO 10545-3

ISO 10545-7

ISO 10545-7

ISO 10545-2

ISO 10545-13

ISO 10545-13

ISO 10545-9

AcuTest



PERFORMANCE DATA

Abrasion Resistance (Glazed)

Dynamic Coefficient of Friction Wet

Chemical Resistance - Household

Chemical Resistance - Acid/Base

Thermal Shock Resistance

CHARACTERISTIC

Water Absorption

Breaking Strength

Dimensions

< 0.5

4/5

0.45

≥ 35 N/mm2

Conforms

Conforms

Conforms



| 1710/1000 |
|--------------|
| NAME OF |
| |
| THE STATE OF |
| A LIPER |
| 程排標 |
| F. Wells |

| TABACCO |
|---------|
| NAME OF |

Frost Resistance ISO 10545-12 Resistance to Stains ISO 10545-14 CUOIO NOTES: Per ANSI standard A108.02,4.3.82, joints on tiles longer than 18" should not be staggered more than 1/3 the length of the tile. Always mix 2-3 cartons at a time while installing to insure the best blend. All product images are representation only.

Resistant Frost Resistant 5 Book An **Appointment**